



Products-

- A. Stabilizer for crushed stone provided by the following manufacturer:
 - 1. Stabilizer Solutions, Inc. 205 South 28th St., Phoenix, AZ 85034; phone (602) 225-5900, (800) 336-2468; fax (602) 225-5902; website stabilizersolutions.com ; e-mail lhubbs@stabilizersolutions.com
 - 1. Decomposed Granite 3/16" crushed aggregate screenings- GreenPro Materials, P.O. Box 265, Bound Brook, NJ 08805; phone (908) 647-0159; fax (908)647-0835; e-mail Ashleigh@greenpromaterials.com

Materials-

- A. Decomposed Granite 3/16" crushed aggregate screenings
 - 1. Crushed Stone Sieve Analysis Percentage of Weight Passing a Square Mesh Sieve AASHTO T11-82 and T27-82

3/16 Minus Aggregate Gradation

U.S. Sieve No.	Percent Passing by Weight
#3/8'	100
#4	90-100
#8	75-80
#16	55-65
#30	40-50
#50	25-35
#100	15-20
#200	10-15